

RASOCAL

READY MIXED SMOOTH-FINISH LIME PLASTER

COMPOSITION

Lime putty compound

PRODUCT PROPERTIES

Pure Lime Putty, selected, free of impurities
Heat resistant

PRODUCT PROPERTIES

Repairs and restoration work.
As a fine smooth finish for plaster and decoration.
For salt-and-pepper effects on fine finish lime plaster.

SUITABLE SUBSTRATES/ BACKGROUNDS – INTERIOR OR EXTERIOR

Prepared plaster surfaces
New finishing plaster/render

METHOD OF APPLICATION

Dampen the substrate with water if excessively dry
Ensure that the surface areas to be treated are free of dust, oil, grease and contaminating substances
Avoid applying at temperatures of less than +5°C and more than +35°C
Apply two coats with a trowel or float to level off the surface
To be finished with a float or spatula, moistening with water if necessary

MAIN PROPERTIES

- | | |
|-----------------------------|---|
| - Specific weight | 1360g/litre |
| - PH | over 12 |
| - Colour | white |
| - Alkali-resistance | no alteration |
| - Hardening | with approx. 3 hours of application – less in high temperatures |
| - Average theoretical yield | 50m ² per 22kg pack |
| - Average consumptionkg | 0.400 kg / m ² |

PACKAGING AND STORAGE

22kg plastic buckets
Store in a cool, dry place, away from frost and direct sunlight

WARNING

Eye and skin-irritant

In the event of eye contact, wash immediately and thoroughly with water, and see a doctor if discomfort is continuous

Keep the packaging out of the reach of children

REMARKS

The current data sheet replaces any previous version.

Our advice and information are given in good faith and depending on the latest developments of our products. We guarantee the consistent quality of our products, but do not accept any liability concerning their application. In any case, we do recommend to consider the type of substrate and the climatic conditions before applying our products or to apply a test surface in order to analyse the suitability of the product for the given substrate.

In case of doubt regarding the substrate, consult our technical service department.